

G151 Datasheet



AQL 1.5

EN445 Parts 1, 2 & 3

ASTM F1671-97

Class 1 Medical Device

MDD 93/42/EEC



General Details

| | |
|--------------------|-------------------|
| Material | Synthetic Rubber |
| Surface Finish | Powder Free |
| Colour | White |
| Geometry | Ambidextrous |
| Texture | Soft Touch Smooth |
| Cuff and Finishing | Beaded |

Glove Specifications

| Size | Weight g/pc | Length mm | Palm Width mm | Thickness | | |
|---|----------------|--------------|------------------|-----------------|-------------|-------------|
| | | | | Cuff | Palm | Finger |
| XS | 4 | 230 | 75 ± 5 | 0.06 ± 0.02 | 0.08 ± 0.02 | 0.11 ± 0.02 |
| S | 4.5 | 230 | 85 ± 5 | 0.06 ± 0.02 | 0.08 ± 0.02 | 0.11 ± 0.02 |
| M | 5 | 230 | 95 ± 5 | 0.06 ± 0.02 | 0.08 ± 0.02 | 0.11 ± 0.02 |
| L | 5.5 | 230 | 105 ± 5 | 0.06 ± 0.02 | 0.08 ± 0.02 | 0.11 ± 0.02 |
| XL | 6 | 230 | 115 ± 5 | 0.06 ± 0.02 | 0.08 ± 0.02 | 0.11 ± 0.02 |
| Tensile strength before ageing (all gloves) | | | | Load @ peak MPA | Min.14 | |
| Tensile strength after ageing (all gloves) | | | | Load @ peak MPA | Min.14 | |

Performance Requirements

| Test | Related Defects | Inspection Level | AQL |
|-----------------------------|-----------------|--------------------------|-----|
| Water Leak at Final Release | Holes | G-1 Single Sampling Plan | 1.5 |

Manufacturing Standards

| | |
|-------------------------|---|
| Manufacturing Standards | Incompliance with ISO 2859 |
| Presentation | Standard: 100 gloves per dispenser box; 10 dispenser boxes per Carton |
| Glove Care | Should not store under direct sunlight or at high heat and humid conditions. Single use only. Avoid high polar solvent. |



G·S·L

WWW.GLOVEMAN.CO.UK

Gloveman Supplies Ltd

Vision House, Treleigh Ind Est,

Redruth TR16 4AX

t. 01209 310734

f. 01209 314760

Soft Touch Synthetic Gloves